

FILM SPECIFICATIONS

THIN CLEAR + MATTE — Rollstock Only

DESCRIPTION

This film is ideal for snack packs and other vertical FFS applications. It processes easily and has a durable seal for transport.

Clear film can create transparent product windows and/or translucent color effects in printed artwork.

Matte finish has low shine, and colors in printed artwork may be slightly muted. Matte clear film will give product windows a “frosted glass”-like effect.

Evaluation and fitness-for-use is the sole responsibility of the customer.

STRUCTURE


Composite: 2.0mil 2-layer laminated film

 Laminate (Exterior) Layer: 1.3mil matte BOPP (Biaxially-Oriented Polypropylene)

 Print + Sealant (Interior) Layer: 70ga clear BOPP

FEATURES

- High clarity with good seal strength
- All materials comply with FDA direct food contact regulations (BOPP: 21 C.F.R. § 177.1520)
- BOPP provides strong seal-to-self fusion with low activation temperature
- BOPP has slip additive for reduced friction on packaging equipment



TYPICAL PROPERTIES

PROPERTY	TYPICAL VALUE	TESTING STANDARD(S)
Total Avg. Thickness (Composite, calculated)	2.0 mil (≈ 50.8 microns)	GB/T 6672 (Laminate layer) Calculated (Print + sealant layer)
Thickness Tolerance	±10 %	
Yield (Composite)	18,406 in ² /lb	
COF (Coefficient of Friction)	≤0.4 (Laminate/exterior surface) ≤0.25 (Sealant/interior surface)	ASTM D1894
Haze (Laminate layer)	≥70 %	ASTM D1003
Gloss (Laminate layer, 45°)	≤8 %	GB/T 8807
Seal/Application Temp. (Print + sealant layer)	200–285 °F 95–140 °C	
Seal Strength (Print + sealant layer, self-to-self)	≥1.1 lb/in	
OTR (Oxygen Transmission Rate)	N/A	
WVTR (Water Vapor Transmission Rate)	≤0.49 g/100 in ² /24 hr	ASTM F1249
Film Shelf Life	12 mo from delivery	
Storage Temperature Range	50–80 °F 10–26 °C	
Storage Humidity Range	30–70 %	

Thin Clear + Matte Spec Sheet v3.3 — Mar 2024

The information provided here is believed to be correct to the best of our knowledge. This information is provided only as a guide, and does not express or imply any guarantees or warranty. It is your responsibility to evaluate the suitability of this material for your intended use prior to using this product. The Packaging Lab assumes no responsibility for the results of use of the products and processes described here. The Packaging Lab reserves the right to modify product properties or composition at any time without notice.